



## **ORIENTAL CARBON AND CHEMICALS LIMITED**

14th Floor, Tower-B, World Trade Tower,  
Plot no. C-1, Sector-16, Noida-201301,  
Uttar Pradesh, India.  
Phone: +91-120-2446850

### **SPECIFICATION SHEET OF** **Diamond Sulf OT-33 (DS-OT-33)**

<b>Description</b>	<b>Product Specification (%)</b>	<b>Test Method</b>
Total Sulphur	66 – 68	ASTM D 4573
Insoluble Sulphur (On Total Sulphur)	90 min	ASTM D 4578
Oil content	32 – 34	ASTM D 4573
Acidity (as H <sub>2</sub> SO <sub>4</sub> )	0.05 max.	ASTM D 4569
Ash content	0.05 max.	ASTM D 4574
Heat Loss	0.50 max.	ASTM D 4571
Fineness Retention (on wet screen)		ASTM D 4572
@ 100 mesh	0.20	
@ 200 mesh	2.00	

**Physical Appearance:** Fine yellow powder.

**Recommended Dosage factor of this grade:** 1.49 x (desired phr of sulphur)

**Shelf – Life :** 1 year from the manufacturing date (subject to the storage in dry ambience and at room temperature)

Date : 16/12/2016