



ORIENTAL CARBON AND CHEMICALS LIMITED

14th Floor, Tower-B, World Trade Tower, Plot No. C-1,
Sector-16, Noida-201301, U.P., India

DIAMIX IS-65 GS

Product Composition: Insoluble Sulphur, Elastomer and Dispersing Agents.

Appearance : Bright yellow Granules

Elastomer : SBR

Typical Values

Total Sulphur % : 66

Insoluble Sulphur % : 59

Elastomer & Dispersing Agents % : 34

Specification

Total Sulphur % : 66±3

Heat Loss (%Max) : 0.5

Density @ 25±2 °C g/cc : 1.45±0.10

Dosage Factor : 1.51 (based on active Sulphur content)

Packing : 25Kg carton boxes

Shelf Life : 365 Days from the date of manufacturing under cool and dry conditions

Insoluble Sulphur, as it is insoluble in rubber, can offer dispersion challenges in rubber compound & components. Diamix IS-65 is a perfect solution for all such challenges. It offers a dust free, eco-friendly & safe alternative to powder Insoluble Sulphur. It is a great product on account of superior dispersion in rubber matrices, easier handling & higher productivity. By using Diamix IS-65 tyre and rubber goods manufacturers can reduce mixing cycle time, reduce scrap rates, avoid losses due to spillages and save on power consumption.