



ORIENTAL CARBON AND CHEMICALS LIMITED

14th Floor, Tower-B, World Trade Tower,
Plot No. C-1, Sector-16, Noida-201301, U.P., India

SPECIFICATION SHEET OF DS 60

Description	Product Specification (%)	Test Method
Insoluble Sulphur	55 min	ASTM D 4578
Soluble Sulphur	45 max	
Ash content	0.20 max.	ASTM D 4574
Heat Loss	0.50 max.	ASTM D 4571

Physical Appearance: Fine yellow powder.

DS 60 is uncoated Insoluble Sulphur grade, which is a mixer of 60% nonoil-coated Insoluble Sulphur and 40 % Rubber Maker Sulphur (RMS).

Shelf – Life : 1 year from the manufacturing date (subject to the storage in dry ambience and at room temperature)

Date : 16/12/2016